

Green-Synthesis, Characterization, and Applications of Nanoparticles (NPs): A Mini Review

Gurumeet Wadhawa¹, Maryappa Sonawale¹,
Anushka Mhatre², Komal Patil², Aditi Gharat², Kajal Kharje², Pranli Satpute², R. F. Inamdar¹
Department of Chemistry, Veer Wajekar ASC College, Phunde¹
Students, Department of Chemistry Veer Wajekar ASC College, Phunde²

Abstract: *Nanobiotechnology is an encouraging and noticeable field of nanotechnology. In recent years, the demands for the synthesis of biocompatible nanoparticles (NPs) are increasing for various applications in different areas such as health, medicine, environmental pollution, and agriculture, etc. A green synthesis of various NPs from different metal/ metal ions using different plant extracts has been extensively studied. Green synthesis of NPs is an alternative way of chemical and physical methods of NPs synthesis and is considered an eco-friendly approach in nanotechnology. Green synthesis of NPs is affected by various factors such as pH, temperature, and incubation time which must be considered to obtain an optimal result. NPs synthesized via green methodology have many potential applications in environment and climate change, biomedical and agriculture. This mini-review provides brief information about different approaches and methods in synthesizing NPs, their characterization by various instrumental applications, and their applications in many areas that are important for humans, animals, and plants*

Keywords: AFM, EDX, Green synthesis, Nanoparticles, TEM, XRD

I. INTRODUCTION

According to the US Environmental Protection Agency (USEPA), nanoparticles (NPs) are usually defined as a particle of matter that is between 1 and 100 nanometres (nm) in diameter. NPs have various physicochemical properties (optical, electrical, magnetic, etc.), such as large surface area, high surface energy, and quantum confinement. Due to these exclusive properties, NPs find countless applications in the electronics, cosmetics, medicine, food, and chemical industry (Pal *et al.*, 2019). Natural NPs are generated in different environmental compartments mineralization, precipitation reactions, physical fragmentation, gas-solid nucleation in the atmosphere, etc. (Sharma *et al.* 2015). Anthropogenic nanoparticles (ANPs) generation result from human-related activity (e.g., combustion), due to the life cycle of products containing NPs or accidental releases; for example, generation of dust by different activities; tillage, mining, and mining construction/demolition. Atmospheric transportation of NPs also done by various processes such as atmospheric release and nucleation release of treated and untreated wastewater and storage in an insufficiently confined area or spreading of sludge from sewage treatment plants (Jun *et al.* 2016). Metallic NPs are generated through different routes comprised of physical, chemical, and biological pathways by two distinct processes a top-down approach and a bottom-up approach (Iravani *et al.*, 2014). NPs are synthesized via size reduction in the top-down approach, whereas in the bottom-up approach, NPs are generated from small entities such as atoms and molecules (Sepur S., 2008). In the green synthesis of NPs, plant or plant parts are used for the bioreduction of metal ions into their elemental nano form (1–100 nm) (Hussain *et al.*, 2016). The process of green synthesis is more efficient, effortless, economical, and can easily be implied to carry out at a large scale (Iravani *et al.* 2014). For the green synthesis of NPs, there is no need to maintain the large culture and it does not create poisonous products (Saravanan *et al.* 2020). Different NPs such as gold, silver, palladium, iron, and zinc oxide (Pal *et al.* 2019) have easily been synthesized through green synthesis. The plants and plant parts contain large amounts of phyto-compounds which are responsible for bioreduction of metallic ions into metal NPs (Saravanan *et al.* 2020).

Approaches for Nanoparticles Synthesis

Chemical, physical and biological methods of NPs generation follow either top-down or bottom-up approaches. In the top-down approach, the relevant bulk material breaks down to fine particles by using suitable mechanic techniques such as sputtering, grinding, and milling. Most of the physical methods come in this approach (Meyers *et al.* 2006). Bottom-up involves NPs generation through the self-assembly of atoms into new nuclei, which further grow into a particle possessing nanoscopic dimensions and employing various chemical and biological methods (Jamkhande *et al.*, 2019).

Biological Method

The biological methods are the synthesis of NPs using bacteria, fungi, algae, or plants. The primary requirements of green synthesis of metal NPs are a metal salt solution and a reducing biological agent. Biological systems (cells) contain reducing agents or other constituents who work as the stabilizing and capping agents, and therefore, no need to add stabilizing and capping agents are required from outside.

Green Synthesis of NPs

As discussed earlier, Green synthesis of NPs means using plants or plant parts to synthesize NPs from their metal compound or salt. Generating NPs through chemical and physical pathways has more chances of toxicity and environmental issues. The chemical method of NPs synthesis is its use of toxic chemicals and solvents, which could harm the environment. The physical pathway demands a bigger space and generates a large amount of heat, increasing the earth surrounding temperature of the source material. Due to these physical and chemical methods, the green synthesis of NPs has got more recognition as an alternative to chemical and physical methods. Green nanotechnology is easy, cost-effective, and eco-friendly and has gained much importance in the recent past. A large number of NPs synthesized via green synthesis approach using microbes, plants, and their size description are presented in Table 1 (Pal *et al.*, 2019).

The General Procedure for Green Synthesis of NPs Plants contains primary metabolites (amino acids, enzymes, vitamins, proteins, carbohydrates, etc.) and secondary metabolites (alkaloids, terpenoids, phenolics, flavonoids, tyannins, etc.). The secondary metabolites play an important role in oxidation/reduction reaction in metal/metal ion suspension which results in the metal NPs. Nowadays, the green synthesis of Ag NPs has gained attention because it is a rapid, non-toxic, eco-friendly, and economical method. During the process of NPs synthesis, the biomolecules (proteins, amino acids, polysaccharides, alkaloids, phenolics, terpenes, saponins, and vitamins) present in plant's extract work as reducing as well as stabilizing agents (Roy *et al.*, 2015). Figure 1 presents the major steps involved in the green synthesis of NPs using various metal/ metal salts.

Conditions Influencing the Green Synthesis of NPs Conditions such as pH, temperature, and reaction time have a major influence on the synthesis and stabilization of NPs using biological sources. The description of each factor is given below.


PH

The pH of the reaction medium plays an important role in the synthesis of NPs (Gericke *et al.*, 2006). The size and shape of the NPs vary due to the different concentrations of hydrogen ions. The larger particles are synthesized at lower pH values than higher pH values (Sathish kumar *et al.*, 2010). For instance, the maximum number of Au NPs (25–85 nm) were synthesized from *Avena sativa* at pH 2, whereas relatively smaller NPs (5–20 nm) were synthesized at pH 3 and 4 (Armendariz *et al.* 2004). The larger size Ag NPs were synthesized at lower pH, whereas dispersed and smaller Ag NPs were synthesized at higher pH using *Cinnamon zeylanicum* bark extract (Sathish kumar *et al.* 2009).

A list of green synthesized NPs and their size using bacteria, fungi, and plants sources (Pal *et al.*, 2019)

SN.	NPs	Sources	Size
1.	Silver	Rhodococcus NCIM 2891	10 nm
2.	Selenium	Escherichia coli, Pseudomonas aeruginosa, Staphylococcus aureus and S. Aureus	90-150 nm
3.	Selenium	Vibrio natriegensas	136 ±31 nm
4.	Gold	Cladosporium cladosporioides fungus isolated from seaweed	>100 nm

5.	Gold	Trichosporonmontevideense	53-12 nm
6.	Lead	Aspergillus	5-20 nm
7.	Zinc oxide	Seaweeds	36 nm
8.	Silver	Reetha and Shikakai leaf extract	~30 nm
9.	Silver	Pongamiapinnata leaf extract	5-15 nm (small) and 22-55 nm(large)
10.	Silver	Azadirachtaindica leaf extract, Chenopodium murale leaf extract	15-35 nm, 30-50 nm
11.	Silver	Chenopodium murale leaf extract	30-50 nm
12.	Gold	Hibiscus leaf extract	16-30 nm
13.	Gold	Trigonellafoenum-graecum leaf extract	15-25 nm
14.	Copper	Cocciniagrandis fruit extract	40-50 nm
15.	SnO2-NP-AC catalyst	Phaseolus lunatus leaf extract	18 nm
16.	Zinc oxide	Rosa canina leaf extract	>50 nm
17.	Zinc oxide	Limoniaacidissima leaf extract	12-53 nm
18.	Zinc oxide	Moringa oleifera leaf extract	16-20 nm
19.	Zinc oxide	Azadirachtaindica leaf extract	9.6-25.5 nm
20.	Zinc oxide	Ocimumbasilicum leaf extract	50 nm
21.	Zinc oxide	Calotropis gigantea leaf extract	30-35 nm



Temperature

Temperature is a stimulating factor in the synthesis of metallic NPs, affecting the shapes and sizes of the synthesized NPs. When Au NPs were formed using *Cymbopogon flexuosus* leaf extract, at lower reaction temperatures (25 to 100°C) nano triangles were formed, whereas spherical NPs along with the nano triangles were synthesized at higher reaction (100° C) temperatures (Raju *et al.*, 2011).

Pressure

The pressure is also an important factor that influences the synthesis of NPs. Pressure affects the shape and size of the NPs synthesis (Abhilash *et al.*, 2012). It has been reported that ambient pressure (1–3 megapascal) reduces the time required to reduce metal ions through a phytochemical agent (Tran *et al.*, 2013).

Incubation Time

The incubation time affects the quality, shape, and size of the NPs (Darroudi *et al.*, 2011). It has been reported that a long incubation time could have resulted in shrinkage or aggregation of NPs, which can cause a limitation in the NPs' potential (Baer 2011).

II. CHARACTERIZATION OF NPS BY VARIOUS INSTRUMENTAL APPLICATIONS

The characterization of NPs provides the knowledge of NPs morphology, composition, and coating. The various instruments used for NPs' characterization are UV-vis spectroscopy, X-ray diffraction; Fourier transforms infrared spectroscopy, Energy dispersive spectroscopy X-ray, Scanning electron microscopy, Transmission electron microscopy, and Atomic force microscopy (Fig. 2) (Fabrega *et al.* 2011). A brief description of each instrument is given below:

Spectrometric Techniques

Spectroscopic techniques give information about the optical properties, state and nature, constitution, and functional groups present on NPs. UV-vis spectroscopy is the primary technique used for the characterization of NPs, and it gives an idea about the particle's aggregation and the optical properties of NPs (Rajsekhar reddy *et al.*, 2010). X-ray diffraction (XRD) gives information about the different phases of a crystalline material and provides NPs dimensions (Hasselov *et al.* 2008). Fourier-transform infrared spectroscopy (FTIR) spectra divulge the functional groups present on the NPs surface during its synthesis (Sankar *et al.*, 2014).

Microscopic Techniques

It is one of the most commonly used techniques generally used to analyse size, shape, and particle aggregation of NPs (Fabrega *et al.* 2011). This technique requires no standard as in other techniques above. The Scanning Electron Microscopy (SEM) gives the images to identify the size and shape of metal NPs. Transmission Electron Microscopy (TEM) is the most efficient and widely used for the characterization of NPs (Sharma *et al.* 2019). TEM images give an idea about the size and aggregation of NPs and the single NPs can be studied by TEM (Sang *et al.* 2014) while SEM cannot access it. Atomic Force Microscopy (AFM) is a high-resolution technique that can be applied for the study of either single NP or aggregated NPs and that are visualized in three (3D) dimensions (Fabrega *et al.* 2011).

III. APPLICATIONS OF NPS IN VARIOUS FIELDS

The demands of NPs are increasing in various fields such as biomedical, cosmetic industries, agriculture, electronics, environment, energy, etc. NPs are of great interest for biomedical sciences, such as silver and gold NPs, the most preferred and frequently used NPs in this field. Gold NPs have been reported for cancer cell detection, protein assay, capillary electrophoresis, and biomarker in a biological screening test; Au NPs also induce apoptosis in B cell- chronic lymphocytic leukemia (Jadoun *et al.* 2020). Engineered NPs are using as growth stimulators that directly or indirectly improve crop production. Nano- fertilizers, nano-pesticides, and sensors have been developed to observe the different agriculture parameters (Usman *et al.* 2020). NPs have been reported for developing specific sensors and detectors to detect pollutants in an open environment, which can remove harmful particles from the air, water, and soil (Aguilar-Pérez *et al.* 2020).

IV. CONCLUSIONS

In recent years, nano-biotechnology has emerged as a major tool for synthesizing NPs that are eco-friendly, non-poisonous, and cost-effective. Various types of NPs from different metals can be synthesized using plant sources, and these NPs have.

REFERENCES

- [1] Dinanath D Patil, Gurumeet C Wadhawa, Arun K Deshmukh, Antioxidant Activity of Hibiscus Ensculatus Linn. International Journal of Pharmaceutical Science and Research ,2 (7) 1464-1466 ISSN :0975-8232
- [2] Vitthal S. Shivankar, *Gurumeet C. Wadhawa, Shakuntala S. Patil Yashwant A. Gaikwad, Tejas Patil, Vaibhav Mali and Laxman V. Gavali PHYTOCHEMICAL ANALYSIS OF THE METHANOL EXTRACT

- FROM LEAVES OF HEMIDESMUS INDICUS European Journal of Biomedical AND Pharmaceutical sciences Volume: 3 Issue: 12 539-543 Year: 2016
- [3] Gurumeet C. Wadhawa*, Vitthal S. Shivankar, Yashwant A. Gaikwad Dhiraj A. Sawant, Mangesh Pingale and Laxman V. Gavali CONVERSION OF COPPER SULPHATE TO COPPER CHLORIDE USING CHLORINE GAS World Journal of Pharmaceutical Research Volume 5, Issue 12, 550-555. ISSN 2277- 7105
- [4] Gurumeet C. Wadhawa1,*, Vitthal S. Shivankar , Shakuntala S. Patil1, Yashwant A. Gaikwad , Aishwarya V. Satere, Bhagyshree Rode1, Charansingh H. Gill and Laxman V. Gavali SYNTHESIS OF 2-SUBSTITUTED BENZIMIDAZOLES AND 1,5-DISUBSTITUTED BENZODIAZEPINES USING ALUM Rasyan Journal of chemistry Vol. 10 No. 1 13-15 January - March 2017
- [5] Gurumeet C. Wadhawa*, Vitthal S. Shivankar, Shakuntala S. Patil Yashwant A. Gaikwad, Dhiraj A. Sawant, Vishal Mane and Laxman V. Gavali CONVERSION OF FERROUS SULPHATE TO FERRIC CHLORIDE USING CHLORINE GAS European Journal of Biomedical AND Pharmaceutical sciences Volume: 3 Issue: 11 288-290 ISSN 2349-8870
- [6] Gurumeet C. Wadhawa, Vitthal S.S. Hivankar, Yashwant A. Gaikwad, Bharat L. Ingale, Basant R., Sharma Shamali S. Hande, Charansingh H. Gill and Laxman V. Gavali ONE-POT SYNTHESIS OF BENZIMIDAZOLES THE PRESENCE OF LEMON JUICE AS A NEW AND EFFICIENT CATALYST EUROPEAN JOURNAL OF PHARMACEUTICAL AND MEDICAL RESEARCH *EJPMR*, 2016,3(12), 556-558 ISSN 2394-3211
- [7] Gurumeet C. Wadhawa*, Vitthal S. Shivankar ,Dinanath D. Patil , Yashwant A. Gaikwad1, Laxman V. Gavali and Chransingh H. Gill REVIEW ON SYNTHESIS OF BENZINMIDAZHARAOLE USING GREEN PROTOCOL Volume 5, Issue 9, 624-656 ISSN 2278 – 4357
- [8] Gurumeet C. Wadhawa, Vitthal S. Shivankar, Yashwant A. Gaikwad, Amit D Surve, Vandana Malusare, Krutika Gawand and Laxman V. Gavali THE EFFECT OF ENZYMES ON RATE AND YIELD OF CURDFORMATION FROM HOMOGENIZED COWMILK. Volume 5, Issue 11, 923-927 ISSN 2278 –4357
- [9] Laxman V. Gavali, Vitthal S. Shivankar, Yashwant A. Gaikwad, Amit Surve Tejas Patil, Vaibhav Mali and Gurumeet C. Wadhawa PHYTOCHEMICAL ANALYSIS OF THE METHANOL EXTRACT FROM LEAVES OF PAULLINIA PINNATA Volume 5, Issue 12, 1673-1683, ISSN 2278 – 4357
- [10] Yashwant A. Gaikwad, Vitthal S. Shivankar, *Gurumeet C. Wadhawa, Shakuntala S. Patil, Sonu K. Singh, Nagesh T. Sankpal and Laxman V. Gavali ANTIOXIDANT EFFECT OF THE STEM AND LEAVES OF *SOLANUM MELONGENA* LINN world journal of pharmacy and Pharmaceutical Sciences Volume 5, Issue 12, 1767-1772 ISSN 2278 – 4357
- [11] Gurumeet C. Wadhawa*, Vitthal S. Shivankar, Yashwant A. Gaikwad Charansingh H. Gill Yogita Mane and Laxman Gavali Antibacterial and Antioxidant, Anti inflammatory study of seed and stem of Delonix Regia Shodhankan 1(1) 2017 ,281-289. ISSN 2250-0383 (National Conference)
- [12] Gurumeet C. Wadhawa*, Vitthal S. Shivankar, Yashwant A. Gaikwad Charansingh H. Gill Bharat Ingale, Shakuntala Patil, Basant Sharma and Laxman Gavali Antibacterial Antioxidant study of zingiberofficinale shodhankan 1(1) 2017 ,298-305. ISSN 2250-0383 ISSN 2250-0383(National Conference)
- [13] Gurumeet C. Wadhawa*, Vitthal S. Shivankar, Yashwant A. Gaikwad Charansingh H. Gill and Laxman Gavali Aishwarya Satare, Krutika Gawand, Vandana Malusare One-pot synthesis of Benzimidazoles the nickel sulphate as new efficient catalyst advanced trends in green chemistry 2017 1(1) 81-83 ISSN 2250-0383(National Conference)
- [14] Pravin Madve, Dhiraj Sawant Gurumeet C. Wadhawa*, Vitthal S. Shivankar, Yashwant A. Gaikwad Charansingh H. Gill and Laxman Gavali. Phytochemical Analysis of the Menthol Extract from leaves of VALLIRINA WALLICH advanced trends in green chemistry 2017 1(1) 30-36 ISSN 2250-0383 G (National Conference)
- [15] Gurumeet C. Wadhawa*, Vitthal S. Shivankar, Yashwant A. Gaikwad Charansingh

- [16] H. Gill and Laxman Gavali. Plant assisted zinc oxide nano particles as catalyst for efficient green one pot synthesis of Benzimidazole Green Chemistry Education 1(1)32-35 ,2017 978-93-84659-81-3 (National Conference)
- [17] Gurumeet C. Wadhawa ,Vitthal S. Shivankar, Yashwant A. Gaikwad , Nilam S. Dhumale, Charansingh H. Gill and Laxman V. Gavali NEW AND EFFICIENT GREEN CATALYST ONE-POT SYNTHESIS OF BENZIMIDAZOLE AND DERIVATIVES World Journal of Pharmaceutical Research Volume 7, Issue 7, 1013-1019 ISSN 2277– 7105.
- [18] Gurumeet C. Wadhawa*, Vitthal S. Shivankar, Yashwant A. Gaikwad Charansingh
- [19] H. Gill and Laxman V. Gavali REVIEW ON ANTIBACTERIAL ACTIVITY OF BENZIMIDAZOLE CONTAINING COMPOUNDS World Journal of Pharmaceutical Research Volume 7, Issue 7, 483-495 ISSN 2277– 7105
- [20] Gurumeet Wadhawa* Yashwant Gaikwad Akashata Singh Nikita Sarwade , Charansingh Gill and Laxman Gavali PLANT ASSISTED ZINC OXIDE NANOPARTICLES FOR SYNTHESIS OF BENZIMIDAZOLE DERIVATIVE European Journal of Biomedical AND Pharmaceutical sciences *EJBPS, 2018, Volume 5, Issue 4, 637-640.* ISSN 2349-8870
- [21] G. C. WADHAWA, S. S. PATIL , Y. MANE , N. SARWADE, C. H GILL Synthesis of benzimidazole Derivatives using Silica as catalyst –Green Approach international journal of chemical and physical sciences *IJCPS Vol. 7, Special Issue ISSN:2319-6602 RICES - Jan 2018*
- [22] C. WADHAWA, V. S. SHIVANKAR, H.WAGH, S. S. PATIL, C.H. GILL1, Y. A. GAIKWAD Green Protocol For Synthesis of 7 (1Hbenzimidazol-2-Y1)-5-(Substituted Phenyl) Pyrido [2, 3-D] Pyrimidin-4-Amine *IJCPS Vol. 7, Special Issue ISSN:2319-6602 RICES - Jan 2018 International Journal of Chemical and Physical Sciences*
- [23] G. C. WADHAWA, S. GITE, D. PATEL, C. H. GILL1, L. GAVALI Facile Synthesis of 2-Substituted Benzimidazoles using Waste Aluminium Foil *IJCPS Vol. 7, Special Issue ISSN:2319-6602 RICES - Jan 2018 International Journal of Chemical and Physical Sciences*
- [24] Charansingh H Gill, Gurumeet C. Wadhawa , Laxman Gavali Vitthal S. Shivankar , Komal Pawar Synthesis of Benzimidazole using waste Magnesium oxide *Research Journal of Pharmacology and Pharmacodynamics* Vol. 10| Issue-03|July- September , 2018
- [25] G.C. Wadhawa *, Harshada Deshmukh , Vitthal S. Shivankar , Yashwant A. Gaikwad ONE-POT SYNTHESIS OF THE COUMARINE UNDER GREEN APPROACH USING FERROUS SULPHATE AS CATALYST *Journal of Pharma Research* Vol. 8, Issue 4, 131-135,2019 ISSN: 2319-5622.
- [26] Abhilash, P. C., Powell, J. R., Singh, H. B., & Singh, B. K. (2012). Plant-microbe interactions: novel applications for exploitation in multipurpose remediation technologies. *Trends in Biotechnology*, 30(8), 416-420.
- [27] Aguilar-Pérez, K.M., Heya, M.S., Parra-Saldívar, R. and Iqbal, H.M. (2020). Nano-biomaterials in-focus as sensing/detection cues for environmental pollutants. *Case Studies in Chemical and Environmental Engineering*, 2, 100055.
- [28] Baer, D. R. (2011). Surface characterization of nanoparticles. *Journal of Surface Analysis*, 17(3), 163-169.
- [29] Brar, S. K., Verma, M., Tyagi, R. D., & Surampalli, R. Y. (2010). Engineered nanoparticles in wastewater and wastewater sludge-evidence and impacts. *Waste Management*, 30(3), 504-520.
- [30] Darroudi, M., Ahmad, M. B., Zamiri, R., Zak, A. K., Abdullah, A. H., & Ibrahim, N. A. (2011). Time-dependent effect in green synthesis of silver nanoparticles. *International Journal of Nanomedicine*, 6, 677.
- [31] Dubey, S. P., Lahtinen, M., & Sillanpää, M. (2010). Tansy fruit mediated greener synthesis of silver and gold nanoparticles. *Process Biochemistry*, 45(7), 1065-1071.
- [32] Fabrega, J., Luoma, S. N., Tyler, C. R., Galloway, T. S., & Lead, J. R. (2011). Silver nanoparticles: behaviour and effects in the aquatic environment. *Environment International*, 37(2), 517-531.

- [33] Gericke, M., & Pinches, A. (2006). Biological synthesis of metal nanoparticles. *Hydrometallurgy*, 83(1-4), 132-140.
- [34] Hassellöv, M, Readman, J. W., Ranville, J. F., & Tiede, K. (2008). Nanoparticles analysis and characterization methodologies in environmental risk assessment of engineered nanoparticles. *Ecotoxicology*, 17(5), 344-361.
- [35] Hussain, I., Singh, N. B., Singh, A., Singh, H., & Singh, S. C. (2016). Green synthesis of nanoparticles and its potential application. *Biotechnology Letters*, 38(4), 545-560.
- [36] Iravani, S., Korbekandi, H., Mirmohammadi, S. V., & Zolfaghari, B. (2014). Synthesis of silver nanoparticles: chemical, physical and biological methods. *Research in Pharmaceutical Sciences*, 9(6), 385.
- [37] Jamkhande, P.G., Ghule, N.W., Bamer, A.H., Kalaskar, M.G. (2019) Metal nanoparticles synthesis: An overview on methods of preparation, advantages and disadvantages, and applications. *Journal of Drug Delivery Science and Technology*, 53:101174.
- [38] Jun, Y. S., Kim, D., & Neil, C. W. (2016). Heterogeneous nucleation and growth of nanoparticles at environmental interfaces. *Accounts of Chemical Research*, 49(9), 1681-1690.