

# Green Synthesis of Silver Nanoparticles from Various Plant Extracts and It's Applications: a Mini Review

Gurumeet Wadhawa<sup>1</sup>, Smita Tandale<sup>1</sup>,  
Komal Patil<sup>2</sup>, Aditi Gharat<sup>2</sup>, Anushka Mhatre<sup>2</sup>, Manali Patil<sup>2</sup>, Shubham Babar<sup>3</sup>

Department of Chemistry, Veer Wajekar ASC College, Phunde<sup>1</sup>  
Students, Department of Chemistry Veer Wajekar ASC College, Phunde<sup>2</sup>

**Abstract:** *Developing environmentally acceptable and reliable nanoparticle production technologies is a crucial step in nanotechnology. Because of their unique chemical, physical and biological properties, Ag NPs have the potential to be used in various ways. As potential agents, biomolecules got from a variety of plant components were used to make it. Despite many academic efforts in the previous decade, synthesizing stability with greater applicability remains a serious challenge. This review reviewed the most recent advancements and breakthroughs in the manufacture of biogenic Ag NPs, as well as their potential uses*

**Keywords:** Silver nanoparticles; Biosynthesis; Nanotechnology; Plant extracts

## I. INTRODUCTION

Nanotechnology is the domain of material science study that is advancing the fastest. Biosynthesis of nanoparticles is becoming a hot topic all across the world. It has emerged into an interdisciplinary approach that deals with nano structured materials (1 - 100 nm). The physiochemical attributes of materials differ considerably than those of equivalent materials in bulk [1].

From ancient methodologies to chemical, medical, and environmental sciences, this field encompasses a wide spectrum of applications. It is playing a critical role with its vast application in nano-medicines, chemical sensing, drug delivery, data storage, cell biology, textiles, food industries, antioxidants, photo catalytic organic dye-degradation, cosmetics, and agriculture and antimicrobial agents [2].

It broadly categorized into organic, which incorporates mainly carbon and inorganic, which incorporates semi-conductor, metallic and magnetic. The production of nanoparticles via conventional methods is toxic to environmental and expensive. With the rising concern for the environment and need for an eco-friendly approach, researches are on a verge of synthesizing nanoparticles using green routes. Bottom-up and top-down techniques to NP synthesis are both viable options [3]. The latter is unpredictable, but while the former causes the self-assembly of atomic-sized particles to produce nano-sized particles that can be transferred via chemical and physical methods.. Green synthesis is cost-effective, proliferate, and cause stable NP creation [4].

Nanoparticles of Gold and Silver furnish superior characteristics and useful flexibility. Silver nanoparticles receive significant interest because of their substantial surface zone with significant potential application in biochemical reactivity and catalytic activity [5]. Biocompatibility has been one of the main reasons for the growing popularity of green technologies. Stabilizer/ capping agent (size controller and agglomeration preventer) synthesis membranes, viral DNA, diatoms, plant extracts, yeast, bacteria, and actinomycetes are widely used [6]. Synthesizes off Ag NPs have been produced from a variety of sources, including microbes and plants, allowing with minimal contamination for industrial production [7].

Plants have been extensively exploited, in contrast to microbes, because their phytochemical show better decrease and stability [8]. It seems to be helpful over electrochemical reduction and heat evaporation.

The essential prerequisite for the production of Ag NPs is Ag<sup>+</sup> ions, which can be made from a variety of silver water-soluble salts; most studies have employed an aqueous AgNO<sub>3</sub> solution with Ag<sup>+</sup> ions in concentrations ranging from 0.1 to 10 mm (most often 1 mm). Due to their broad array of applications, such as cancer diagnosis and treatment, significant interest in synthesis or production of Ag NPs has always been in the scientific community [9]. The Ag NPs have piqued researchers' curiosity in the past because of their organic and physio-chemical properties.. It has high thermal conductivity, chemical stability, catalytic and nonlinear optical behaviour which allows having the ability to value in inks, microelectronics, and clinical imaging [10].

Plant extract which receives plenty of attention for the simplicity, rapid synthesis with removal of detailed maintenance in cell cultures with eco-friendliness mediates the most sophisticated method for synthesizing nano-particle. Ag NPs biosynthesis is carried out through plants as they have necessary reducing agents like flavonoids, citric acid, ascorbic acids, reductases, saponins. Dehydrogenases and extracellular electron shutters are also involved in metallic Ag NPs biosynthesis. Present review draws an attention regarding Ag NPs biosynthesis using different plant extract material which enables the researchers as a potential source of green synthesis of nanoparticle.

## II. SYNTHESIS OF SILVER NANOPARTICLES

### 2.1. Physical synthesis

Top-down process refers to micro fabrication where gears are used to cut, mill and shape substances into a particular shape (Fig. 1). Lithography and laser ablation reduce the scale of silver metal robotically to the nano-scale [11]. The formation of nano-structured materials has fewer defects and many equivalent chemicals with a brief and long variety of ordering [12]. In the top to backside process, evaporation–condensation primarily synthesized NPs in the furnace.




Figure 1 Biogenic synthesis of nanoparticles

In this approach, they confined the base materials inside a boat and vaporized into carrier gas in the furnace's center point. Ag, Au, PbSO<sub>4</sub>, CdS and fullerene nanoparticles formerly produced by use of the evaporation or condensation approach. Several demerits are seen when synthesis of Ag NPs are done using a tube furnace [13]. To achieve a consistent working temperature, a conventional tube furnace consumes hundreds of kilowatts of energy and requires tens of minutes of preheating time. Silver nanoparticles were indeed produced with less solution ablation of metal bulk materials [14]. As a result, laser ablation has an advantage over other conventional methods of generating metallic colloids in the absence of chemical reactions in solutions. So natural colloids, with the intention to be beneficial for similar packages, can be produced via this method [15].

### 2.2. Biological synthesis

The silver nanoparticles synthesis by physical and chemical methods is highly expensive. Nano particles from chemical synthesis are not medically suitable as they have absorbed toxic substances absorbed onto their surfaces. In order to get commercialized, it must cost the nanoparticles effective. In order to get an economically workable method and environmentally sound, researchers have pursuit such alternative synthesis method by investigating on biological substances. They discovered nanoparticles made from microorganisms and plant extracts are more cost-effective and act as reducing and stabilizing agents. Microbial enzymes and plants with oxidation or reduction characteristics are used to make nanoparticles in green biotechnology [16] (Fig. 2).




Figure 2 Schematic diagram of green synthesis of silver nanoparticles

### 2.3. Ag NP Synthesis in Plants

To synthesize Ag NPs, plant extracts were being used and because of their availability, low toxicity, and safety, they may be preferable to bacterial and fungal synthesis [16]. Ag NPs' properties are determined by the plant extract sources. Individual phytochemical and phytochemical combinations in extracts differ substantially depending on the plant source [17]. As a result, changing the extract composition can change the characteristics of Ag NPs [18]. For biosynthesis, an aqueous AgNO<sub>3</sub> solution is mixed with an aqueous plant extract at an ambient temperature only for a few minutes [19]. Large amounts of phytochemical capable of producing Ag NPs have been identified [20]. Plants with functional groups, including hydroxyl, aldehyde, ketone, carboxyl, and amino can decrease Ag<sup>+</sup> ions [21]. The specific method of Ag NPs synthesis differs depending to phytochemical variety. Specific functional groups reduce the Ag<sup>+</sup> ion, which is one of the key processes. The hydroxyl groups in all the compounds allow Ag<sup>+</sup> ions to be reduced, resulting in Ag NPs production [22]. Phytochemical are not all the same, which is surprising. Only a few phytochemical discovered from plant extracts reduce Ag<sup>+</sup> ions. A wide range of plants include phytochemical, which

serve as an organic reducing agents. And according to the study flavonoids are only responsible for Ag NPs synthesis. (Fig.3).



Figure 3 Synthesis of Ag NPs by reaction of AgNO<sub>3</sub> with photochemical

## 2.4. Synthesis of silver nanoparticles from various plant extracts

### 2.4.1. Aloe vera nanoparticles

Recent study on aloe vera plant has given rise to In<sub>2</sub>O<sub>3</sub> (Indium Oxide) nanoparticles with particles size ranging from 5 to 50 nm. This is cost effective and eco-friendly. Calcinations get these nanoparticles, the dried In<sub>2</sub>O<sub>3</sub> precursor in a hot air oven at 400-600°C for 2 hours. As it is characterized by XRD (X-ray diffraction) (Pw 3040) with Cu K $\alpha$  radiation ( $\lambda = 0.15406\text{nm}$ ) and TEM analysis [23]. Aloe Vera plant extracted solution synthesized an extremely adopting cost effective precursor for preparation of In<sub>2</sub>O<sub>3</sub> nanoparticles. It successfully synthesized Au NPs in a single crystalline triangular form (~ 50 - 350 nm) and Ag NPs in spherical form (~15nm) to be used for other biomedical approaches.

Half of the Ag NPs generated with aloe-vera extract had mosquitocidal and antibacterial properties [24], which is a benefit. At low doses, the LC<sub>50</sub> of aloe-vera Ag NPs evaluated against *An. stephensilarvae* and pupae was 3.825 ppm. After 24 hours, 48 hours, and 72 hours, aloe-vera synthesised Ag NPs (10  $\times$  LC<sub>50</sub>) reduce *An. stephensi* larvae reduction to 74.5, 86.6, and 97.7%, respectively, under outdoor circumstances. Aloe vera leaf extract synthesised silver nanoparticles showed greater fungicidal activity against *Rhizopus* sp. and *Aspergillus* sp. [25] on the application of 100  $\mu\text{L}$  of 1 M silver nanoparticles.

### 2.4.2. Citrus lemon (lemon) nanoparticles

Citrate and ascorbic acid act as reducing agents to make Ag NPs and Au NPs [26]. As lemon content is both types of acids, it is reliable to produce a green synthesis of nanoparticles. It took varieties of concentration of silver nitrate solution (10<sup>-2</sup> M, 10<sup>-3</sup> M and 10<sup>-4</sup> M) which are interacted with lemon juice with a different ratio for a different time in 30°C within a rotary shaker of 120 rpm. After centrifugation of 10000 rpm for 10 minutes, separate the pellet and then freeze-dried using lyophilizer to harvest. UV visible spectroscopy, X-ray diffraction, Fourier transform infrared spectroscopy, Atomic force microscopy, and Transmission electron microscopy (TEM) were used to characterise this. These Ag NPs are spherical and spheroidal (< 50 nm).

On cotton and silk materials, the extracted silver nanoparticles provided a long-lasting textile finish [27]. Because of the synergistic action of Ag<sup>+</sup> and lemon leaves, essential oil components convert Ag<sup>+</sup> ion to Ag<sup>0</sup>. Ag NPs generated has high antimicrobial activity. It inhibits *Fusarium oxysporum* and *Alternaria brassicicola* growth on agar diffusion medium. FT- IR was used to studying the formation [28]. Lemon extraction was made and combined with the solution, which was monitored using a spectrophotometer, FESEM, and EDAX analysis. Dermatophytosis patients' skin scales were treated with this lemon-derived Ag NPs were found to have anti-dermatophyte action and also cost-effective.

#### 2.4.3 Menthaasiatica (Mint) nanoparticles

*Menthaasiatica* has a good inhibitory activity in a bactericidal action against *Escherichia coli* and *Pseudomonas aeruginosa*, with gram-negative bacteria. It started the process with extract suspension of mint leaf treated with AgNO<sub>3</sub>, 20 minute it changes colour to white and after proper incubation of 5 hr gives outcome of silver nanoparticles [29]. This is characterized by spectral analysis showing SPR in 200 to 600 nm. These Ag NPs have the ability of antimicrobial, antimalarial, antidiabetic, antioxidant and anticancer pastime.

Ag NPs from mint extract (5 -50 nm) is achieved by various physio-chemical and organic techniques. Bio-reduction is achieved using Au NPs with a spherical and triangular shape (3–26 nm). *Menthapiperita* leaf extract act as a reducing agent for synthesis of Au NPs. The content of leaf extract regulated it, as well as the time and temperature factors. With a leaf extract concentration of 1.5% (leaf extract) at 70°C for 3 minutes, the best bio reduction was achieved [30].

Produce Ag NPs are toxic and hazardous for microorganism which helps in the drug delivery system in medicine. NPs from the *Mentha* species extract are active against six bacteria: *Bacillus fastidiosus* (the highest inhibitory effect), *Proteus mirabilis*, *P. vulgaris*, *Salmonella choleraesuis*, *Escherichia coli*, *Pseudomonas aeruginosa*, *Klebsiella pneumoniae* and *Serratiaodorifera* except for *Staphylococcus aureus*.

#### 2.4.4. Ginger nanoparticles

Ginger extract Copper nanoparticles are mostly multifunctional inorganic nanoparticles have a capacity of heavy antibacterial activity in gram-positive bacteria [31] green synthesised Cu NPs with sizes of 40 and 25 nm, respectively. *Ginger* root is rhizome of a plant *Zingiber officinale* which is mostly used for copper nanoparticle formations. The plant was crossed and dispense in 10 ml of sterile distributor undated for 23 minutes at 70°C extract filtered using whattman filter paper, then sterilize method is applied on it. Then 1:1 of CuSo<sub>4</sub> solution to get nanoparticles. For silver nanoparticles production the Ag<sup>+</sup> and AuCl<sub>4</sub><sup>-</sup> ions. 5 ml of ginger rhizome broth at room temperature was added to AgNO<sub>3</sub> and HAuCl<sub>4</sub> solution (1.0×10<sup>-3</sup> M) of 50 ml separately, incubated in dark in a shaker at 120 rpm at 37°C. A UV- visible spectrophotometer can conveniently monitor the bio-reduction of aqueous Ag<sup>+</sup> and AuCl<sub>4</sub><sup>-</sup> ions [32]. Produced Gold nanoparticles are of 5-20 nm whereas silver nanoparticles are 35-46 nm. Biosynthesis of multiple shaped Au NPs from *Colletotrichum sp.*, which grows on geranium leaves, was studied [33].

The ginger-derived nanoparticle (GDN) was employed to activate nuclear factor erythroid 2-related component 2 (Nrf2), which triggered the expression of a set of liver detoxifying/antioxidant genes while suppressing reactive oxygen species generation [34]. Ginger protects the liver from the hepatotoxic effects of carbon tetrachloride, ethanol, and acetaminophen. As a result, the nanoparticle made from ginger could be used as a new liver-protective agent.

#### 2.4.5. Hibiscus Rosa nanoparticles

Zinc Oxide nanoparticles are synthesis by the bio components of leaves extract of *Hibiscus Rosa sinensis*. These nanoparticles are multifunctional, inorganic and crystalline, simple and eco-friendly methods synthesized this. Zinc oxide a nanoparticle biosynthesis was carried out from *Hibiscus Rosa* leaf extract of has used for a reducing material as well as stabilizing material for [35]. 5 g of fine washed dried leaves powder with 100 ml double distilled water, which were utilised for the reduction of Zn<sup>2+</sup>, zinc nanoparticles (ZnO). After boiling for 60-80 minutes, add 5 g zinc nitrate and watch the colour change. They then roasted the pest in a furnace for two hours at 400 degrees Celsius, resulting in a light yellow powder. Between 30 and 35 nanometers are the sizes of the ZnO crystallites.

The nps are characterized by TEM, XRD and FTIR spectroscopy [36]. PH fluctuation of medium affects distinct shape of Ag NPs. FTIR analysis has shown that the Au NPs are bound to amine groups and the Ag NPs to carboxylate ion groups. The SEM analysis reveal the particle to be spherical and size ranges from 5 to 40 [37]. Ag NPs have essential applications in medicine on antimicrobial agent. They have effective bactericidal against *Catlatcatla* fish infected with *Aeromonas hydrophila*.

### III. CHARACTERIZATION OF SILVER NANOPARTICLES

Researchers typically use centrifugation to gain pellet or powder form of generated Ag NPs which are oven dried. They did Ag NPs characterisation using UV-Vis Spectra, SEM, TEM, FTIR, XRD, and EDAX [38]. DLS instead of plant and microbes is commonly utilised for Ag NPs made from biopolymers. Zeta potential is determined for Ag NPs stability. Ag NPs stability and organic composition due to AgNO<sub>3</sub> and L-cystine influence was determined using TGA [39]. ICP analysis was carried out to investigate Ag NPs concentration and conversion [40]. The synthesised Ag NPs' SPR peak was observed in the 400-450 nm regions, which is the important range for Ag NPs [41]. The size-stability of manufactured Ag NPs has been revealed using UV-Vis spectral studies, a shift in a red peak in the SPR peak shows an increase in size and blue peak reveals vice versa. The creation of face-centred cubic (FCC) crystalline structured Ag NPs with Ag weight ranging from 45% - 80% demonstrate demonstrated by almost all the studies using XRD measurements. Cubic and hexagonal forms have been reported in several cases.

A 45% - 80% Ag weight EDS or EDAX optical absorbency band determines nanomaterials elemental composition to be around 3 Ke V. Of the all circumstances observed the stability of synthesised nanoparticles to range from 1 day to 1 year.

### IV. VARIOUS APPLICATIONS OF SILVER NANOPARTICLES

The silver nanoparticle has many applications in medical, industrial, pharmacological (like anti-microbial activity, antibacterial property, and anti-fungal activity etc. and environmental. It plays a major role in disinfecting of medical devices and water treatment [42]. Currently, nano materials are used in the prevention, diagnosis and treatment of most cancers the usage of photo-based therapeutic applications [43] with little irradiation energy density nanostructures are effective in destroying the most cancers cells than non-most cancers cells [44].

### V. PHARMACOLOGICAL APPLICATION

#### 5.1. Anti-bacterial activity

It may significantly assimilate Ag NPs into biosensor materials, antimicrobial applications, wound healing, cosmetics, textile industry, etc. They are significant in the sector of medicine and biology because of their antimicrobial actions on pathogens [45]. Antimicrobial agent silver has been known for centuries; the latest resurgence interest for this element especially makes a speciality of the increasing risk of antibiotic resistance, due to the wrong use of antibiotics [46] Development of antibiotic resistance amongst bacteria, it is necessary to make that alternative antibacterial therapy. The Ag NPs release classical bactericidal towards both Gram-positive and negative [47]. The antimicrobial pastime might be because of either (i) pore formation in mobile wall ending in a long run as leakage of cellular content material or (ii) the Ag<sup>+</sup> perforate thru ion channels does no harm to the membranes; instead denatures the ribosome, hold back the enzymatic expression and thiol proteins necessary in manufacturing ATP and DNA leading to elimination [48].

#### 5.2. Anti-fungal activity

Ag NPs are sophisticate and effective fungicides towards an extensive range of fungal sp. which includes *Aspergillus*, *Candida* and *Saccharomyces* [49]. Ag NPs of *Withania sominifera* have shown antifungal against fungal pathogens like *A. Niger*, *A. flavus* and *C. albicans* [50]. Recently, research found antifungal from Ag NPs from Tulsi (*Ocimum sanctum L.*) against opportunistic human fungal pathogen [51]. It took Ag NPs into consideration as an effective fungicidal against fungi, inclusive of *Aspergillus*, *Candida* and *Saccharomyces*.

#### 5.3. Medical devices and water treatment

Ag NPs are used predominantly in ointments not only used to prevent but with healing activity towards wounds, burns and infections [52, 53]. They may recruit for water purification and filtering apparatus due to its superior antimicrobial nature [42]. Silver nanoparticle is used for purification of water by stopping the growth of pathogenic microbes through editing or coating the floor. It is accepted with much consideration for biomedical gadgets and in FMCG industries. The coating has to possess effectiveness, easy fabrication of lower toxicity [54]

#### 5.4. Catalytic activity

The reduction of the methylene blue was significantly achieved by filtered aqueous extract of *Terminalia chebula* fruit powder [55] besides draw out of *Acacia nilotica* pod mediated Ag NPs altered glassy carbon electrode confirmed extra catalytic interest on the discount of benzyl chloride which is compared to [56] the ones of glassy carbon and metallic.

#### 5.5. Anticancer in Vitro

Techniques for preparing anti-cancer Ag NPs are now being studied in depth. Ag NPs made from biological sources showed considerable inhibitory action against the survival of various malignant cell lines. The reducing agents in those approaches were plants components extracts (e.g., leaf, root, flower, or fruit). The HNGC2 cell line, which is brain cancer, was reported to be inhibited by biosynthesized Ag NPs [57]. These spherical Ag NPs have IC50 values ranging from 20 to 80 nm in a dose-dependent manner [58]. The cervical cancer cell lines Siha and He La were found to be inhibited by biosynthesized Ag NPs. 2–18 nm triangular and hexagonal Ag NPs with an IC50 of 4.25 g/mL reduced the Siha cancer cell line's proliferation [59]. Ag NPs inhibited He La cancer cell lines with diameters ranging from 5 to 120 nanometers. The Ag NPs manufacturing technique and plant extracts employed influenced the IC50 values. Hexagonal Ag NPs with an IC50 of 4.25 g/mL. The biosynthesised Ag NPs inhibited four colon cancer cell lines with IC50 values ranging from 5.5 to 100 g/mL [60]. With diameters ranging from 7.39 to 80 nm, the particles were essentially spherical. Cuboidal and spherical bio-Ag NPs (59 -94 nm) have IC50 values between 78.58 - 83.57 g/mL, inhibiting A431 and epidermoid cancer cell line [61]. Spherical Ag NPs inhibited a cell line of liver cancer (6.4 to 1200 nm) (Hep-G2).

Spherical bio-Ag NPs (< 20 nm) inhibit the intestinal Caco-2 cancer cell line, having an IC50 value of > 30 g/ml. Spherical Ag NPs (< 40 nm 95) suppressed the Hek-293 kidney cancer in a dose-dependent manner.

Size and form of Ag NPs affect their cytotoxicity. The most interesting practical reason is that Ag NPs of this size and shape may come into direct contact with cell surfaces, causing cytotoxicity. NPs are safe at low concentrations, but they can be dangerous at high doses. Angiogenesis is the formation of new blood vessels from existing ones, which is vital for tissue nutrition and waste removal [62]. Solid tumours are aided by new blood vessels formation [63]. This process is controlled by activator and inhibitor molecules, which act as crucial in cancer spread. Oxygen and nutrients supply to cancer cells aids the tumour growth, allowing infiltrating and metastasis [64]. As Ag NPs change per inhibiting factor-induced RNV in vascular endothelial cells and block extracellular signal-related kinase. Ag NPs anti-angiogenesis properties are used to treat cancer by a various means. The cell cycle is a complicated network of signalling pathways that enables a cell to divide and replicate its DNA. This phenomenon is important in the progression of cancer. This natural system breaks down when cancer develops genetic mutations, resulting in uncontrollable proliferation. The cell arrest checkpoints are DNA synthesis, mitosis, G1 and sub G1. Ag NPs has shown the cell cycle to stop in the sub-G1 phase, explaining the relationship between sub-G1 phase arrest and apoptosis in cancer cells [65]. The development of the pro-apoptotic protease caspase-3 is associated with increasing cancer cell numbers in the sub-G1 phase [66]. Ag NPs have been extremely hazardous to mammalian cells in the past [67]. The risk of toxicity is present when metal is converted into its nano form. Green synthesis, on the other hand, minimises Ag NP toxicity. The usual toxicity of a substance is largely determined by its covering. Green synthesis Ag NPs are ideal for a variety of medical applications due to their coating [68].

## VI. FUTURE ASPECTS OF AG NPS BY PLANTS

Green chemistry, though non-toxic, low-cost and ecofriendly the biological approaches, has substantial limitations. Ag NPs high biodegradability and clearance aid in the prevention of toxicity. Ag NPs have proven as potential nanomedicine-based therapeutics. Clinical trials using Ag NPs-based nanomedicine are needed to determine the application's future direction. Clinical trials must address issues like as biodegradability, dosage, and administration method. Something can also utilise Ag NPs to visualise and detect cancer cells in the early stages of the disease. The ability of green Ag NP production to aid in vivo fluorescent tumour imaging has already been showed [69].

**Abbreviations**

Ag NPs; Silver Nanoparticles  
G: Grams  
UV: ultraviolet  
FESEM Field emission scanning electron microscope  
EDAX: Energy Dispersive X-Ray Analysis  
Ag: Silver  
Au NPs: Gold Nanoparticles  
Au: Gold  
Cu: Copper  
NP: Nanoparticles  
SEM: Scanning Electron Microscope  
IC50: Half maximal inhibitory concentration  
RPM: Rotation per minute  
XRD: X-ray Diffraction analysis  
SPR: Surface Plasmon resonance  
TGA: Thermo-Gravimetric Analysis  
ICP: Inductive Coupled Plasma

**VII. CONCLUSION**

To develop green synthesis, many efforts have been made since last decade. Nature has developed the most capable and ingenious small helpful materials. A rising understanding of green chemistry and the utilisation of green pathways for manufacturing metal NPs, particularly Ag-NPs, provided the impetus for developing environmentally friendly methodologies. Plants that produce Ag-NPs have an advantage over other biological entities in that they can overcome the slow process of employing microbes and maintain their culture, which can lose their ability for NPs production. The advantages of synthesis from plant extracts include a sanitary working environment, health and environmental protection, less waste, and the most stable products. There is a disparity in the results that will require extra work to correct. Ag NPs offer a lot of potential in cancer therapy as drug carrier, metabolites biosensors and pollutants, catalysts, cardiovascular implants, dentistry, medicine, and therapeutics, to name a few applications.

**Compliance with ethical standards**

**Acknowledgments**

The authors intend to show a deep sense of gratitude to the Honorable President Dr. Manoj Ranjan Nayak, Siksha 'O' Anusandhan, deemed to be University for permitting to publish scientific literature.

**Authors' Contributions**

Arun Kumar Pradhan did the investigation and writing of the original draft manuscript. Sameer Ranjan Sahoo and Swapnashree Satapathy did the review of final manuscript, editing of the original draft manuscript and supervision. Snehalata Pradhan and Jyoti S. Prusty did the visualization, resource acquisition, and supervision. Subham Preetam did the diagram preparation. Arun Kumar Pradhan did the overall supervision. All the authors reviewed the manuscript and given consent for submission. Arun Kumar Pradhan shares the senior authorship.

**Disclosure of conflict of interest**

On behalf of all authors, the corresponding author states that there is no conflict of interest.

**REFERENCES**

- [1] Jahn W. Review: chemical aspects of the use of gold clusters in structural biology. *J Struct. Biol.* 1999; 127; 106– 112.
- [2] Mansoori, GA. Principles of nanotechnology: molecular-based study of condensed matter in small systems. *World Scientific*, Singapore. 2005.
- [3] Arole V, Munde S. Fabrication of Nanomaterials by Top-down and Bottom-up Approaches- An overview, *J Adv Appl Sci Technol.* 2014; 1; 89–93.
- [4] Thakkar KN, Mhatre SS, Parikh RY. Biological synthesis of metallic nanoparticles. *Nanomedicine.* 2016; 6; 257– 262.
- [5] Vadlapudi V, Kaladhar D. Review: green synthesis of silver and gold nanoparticles, *Middle East J Sci Res.* 2014; 19; 834–842.
- [6] Daphne J, Francis A, Mohanty R, Ojha N, Das N. Green Synthesis of Antibacterial Silver Nanoparticles using Yeast Isolates and its Characterization, *Res J Pharm Technol.* 2018; 11; 83–92.
- [7] Xu ZP, Zeng QH., Lu, GQ, Yu AB. Inorganic nanoparticles as carriers for efficient cellular delivery. *Chem Eng Sci.* 2006; 61; 1027–1040.
- [8] 2006; 61; 1027–1040.
- [9] Mohamad NAN, Arham NA, Jai J, Hadi A. Plant Extract as Reducing Agent in Synthesis of Metallic Nanoparticles: A Review, *Advanced Materials Research.* 2014; 832; 350-355.
- [10] Popescu M, Velea A, Lőrinczi A. Biogenic production of nanoparticles, *Digest journal of nanomaterials & biostructures.* 2010; 5; 4.
- [11] Edison TJJ, Sethuraman MG. Biogenic robust synthesis of silver nanoparticles using *Punica granatum* peel and its application as a green catalyst for the reduction of an anthropogenic pollutant 4-nitrophenol". *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy.* 2013; 104; 262-264.
- [12] Tolaymat TM, El-Badawy AM, Genaidy A, Scheckel KG, Luxton TP, Suidan M. An evidence-based environmental perspective of manufactured silver nanoparticle in syntheses and applications: a systematic review and critical appraisal of peer-reviewed scientific papers. *Science of the total environment.* 2010; 408; 999-1006.
- [13] Leela A, Vivekanandan M. Tapping the unexploited plant resources for the synthesis of silver nanoparticles, [14] *African Journal of Biotechnology.* 2008; 7; 17.
- [15] Samberg ME, Oldenburg SJ, Monteiro-Riviere NA. Evaluation of silver nanoparticle toxicity in skin in vivo and keratinocytes in vitro, *Environmental health perspectives.* 2010; 118; 407-413.
- [16] Dolgaev SI, Simakin AV, Voronov VV, Shafeev GA, Bozon-Verduraz F. Nanoparticles produced by laser ablation of solids in liquid environment. *Applied surface science.* 2002; 186; 546-551.
- [17] Tsuji T, Iryo K, Watanabe N, Tsuji M. Preparation of silver nanoparticles by laser ablation in solution: influence of laser wavelength on particle size. *Applied surface science.* 2002; 202; 80-85.
- [18] Prabhu S, Poulouse EK. Silver nanoparticles: Mechanism of antimicrobial action, synthesis, medical applications, and toxicity effects, *Int. Nano Lett.* 2012; 2; 32.
- [19] Ramasamy, M., Lee, J.H., Lee, J., 2017. Direct one-pot synthesis of cinnamaldehyde immobilized on gold nanoparticles and their antibiofilm properties. *Colloids Surf. B Biointer faces.* 160, 639–648.
- [20] Mukunthan, K., Balaji, S., 2014. Cashew apple juice (*Anacardium occidentale* L.) speeds up the synthesis of silver nanoparticles. *Int. J. Green Nanotechnol.* 4, 71–79.
- [21] Mittal AK, Chisti Y, Banerjee UC. Synthesis of metallic nanoparticles using plant extracts. *Biotechnol. Adv.* 2013; 31; 346–356.
- [22] Sathishkumar P, Vennila K, Jayakumar R, Yuso ARM, Hadibarata T, Palvannan T. Phyto-synthesis of silver nanoparticles using *Alternanthera tenella* leaf extract: An elective inhibitor for the migration of human breast adenocarcinoma (MCF-7) cells. *Bioprocess Biosyst. Eng.* 2016; 39; 651–659.

- [23] Jasuja ND, Gupta DK, Reza M, Joshi SC. Green Synthesis of Ag NPs Stabilized with bio-waste and their antimicrobial activities. *Braz. J. Microbiol.* 2014; 45; 1325–1332.
- [24] Schaer B, Hohenester U, Trügler A, Hofer AF. High-resolution surface plasmon imaging of gold nanoparticles by energy-filtered transmission electron microscopy. *Phys. Rev. B.* 2009; 79; 4-14.
- [25] Maensiri, S., 2008. Indium oxide (In<sub>2</sub>O<sub>3</sub>) nanoparticles using Aloe vera plant extract: Synthesis and optical properties. *Optoelectronics and advanced materials.* 2, 161–165.
- [26] Devakumar D. Mosquitocidal and antibacterial activity of green-synthesized silver nanoparticles from Aloe vera extracts: towards an effective tool against the malaria vector *Anopheles stephensi*. *Parasitology Research.* 2015; 114; 1519–1529.
- [27] Shreya M. Biosynthesis of silver nanoparticles from *Aloe vera* leaf extract and antifungal activity against *Rhizopus* sp. and *Aspergillus* sp. *Applied Nanoscience.* 2015; 5; 875–880.
- [28] Prathna TC. Biomimetic synthesis of silver nanoparticles by Citrus lemon (lemon) aqueous extract and theoretical prediction of particle size. *Colloids and Surfaces B: Biointer faces.* 2011; 82, 152–159.
- [29] Padma SV. Biosynthesis of silver nanoparticles using lemon leaves extract and its application for antimicrobial finish on fabric. *Applied Nanoscience.* 2012; 2; 163–168.
- [30] Najia Nisha S. Lemon peels mediated synthesis of silver nanoparticles and its anti dermatophytic activity.
- [31] *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy.* 2014; 124; 194-198.
- [32] Diptendu S, Goutam P. Green Synthesis of Silver Nanoparticles using *Mentha asiatica* (Mint) Extract and Evaluation of their Antimicrobial Potential. *Int. J. Curr. Res. Biosci. Plant Biol.* 2017; 4; 77-82.
- [33] Germán AV. Synthesis and characterisation of gold nanoparticles using *Mentha piperita* leaf extract: a green, non-toxic and rapid method. *Int. J. Nano and Biomaterials.* 2014; 5; 181-192.
- [34] Issu Ipsa S. Antimicrobial Activity of Copper Nanoparticles Synthesised by Ginger (*Zingiber officinale*) Extract. *World Journal of Nano Science & Technology.* 2016; 2; 10-13.
- [35] Chandan S. A green biogenic approach for synthesis of gold and silver nanoparticles using *Zingiber officinale*. *J. Nanomaterials and Biostructures.* 2011 6, 535-542.
- [36] Shankar SS, Ahmad A, Pasricha R, Sastry M. Bioreduction of chloroaurate ions by geranium leaves and its endophytic fungus yields gold nanoparticles of different shapes. *Journal of Materials Chemistry.* 2003; 13; 1822- 1826.
- [37] Xiaoying Z. Ginger-derived nanoparticles protect against alcohol-induced liver damage. *Journal of Extracellular Vesicles.* 2015; 4; 2347 – 5161.
- [38] Sharmila Devi R, Gayathri R. Green Synthesis of Zinc Oxide Nanoparticles by using *Hibiscus rosa-sinensis*.
- [39] *International Journal of Current Engineering and Technology.* 2014; 4; 2277 – 4106,
- [40] Daizy P. Green synthesis of gold and silver nanoparticles using *Hibiscus rosasinensis*. *Physica E: Low-dimensional Systems and Nanostructures.* 2010; 42; 1417-1424.
- [41] Surya S. Green Synthesis of Silver Nanoparticles from Flower Extract of *Hibiscus rosa-sinensis* and Its Antibacterial Activity. *International Journal of Innovative Research in Science, Engineering and Technology.* 2016; 5; 5242-5247.
- [42] Sre PR, Reka M, Poovazhagi R, Kumar MA, Murugesan K. Antibacterial and cytotoxic effect of biologically synthesized silver nanoparticles using aqueous root extract of *Erythrina indica* lam. *Spectrochim. Acta Part A Mol. Biomol. Spectrosc.* 2015; 135; 1137–1144.
- [43] Perni S, Hakala V, Prokopovich K. Biogenic Synthesis of Antimicrobial Silver Nanoparticles Capped with L-Cystine.
- [44] *Colloids and Surfaces A: Physicochemical and Engineering Aspects,* 2014; 460; 219-224.
- [45] Song JY, Kim BS. Rapid Biological Synthesis of Silver Nanoparticles Using Plant Leaf Extracts. *Bioprocess and Biosystems Engineering.* 2009; 32; 79-84.

- [46] Sastry M, Mayyaa KS, Bandyopadhyay K. pH Dependent Changes in the Optical Properties of Carboxylic Acid Derivatized Silver Colloid Particles. *Colloids and Surfaces A: Physicochemical and Engineering Aspects*. 1997; 127; 221-228.
- [47] Jain P, Pradeep T. Potential of silver nanoparticle-coated polyurethane foam as an antibacterial water filter, *Biotechnology and bioengineering*. 2005; 90; 59-63.
- [48] Menon JU, Jadeja P, Tambe P, Vu K, Yuan BH, Nguyen KT. Nanomaterials for photo-based diagnostic and therapeutic applications. *Theranostics*. 2013; 3; 152–166.
- [49] Wu P, GAO Y, Lu YM, Zhang H, CAI CX. High specific detection and near-infrared photothermal therapy of lung cancer cells with high SERS active aptamer-silver-gold shell-core nanostructures. *Analyst*. 2013; 138; 6501–6510.
- [50] Rajakannu S, Shankar S, Perumal S, Subramanian S, Dhakshinamoorthy PG. Biosynthesis of silver nanoparticles using *Garcinia mangostana* fruit extract and their antibacterial, antioxidant activity. *Int. J. Curr. Microbiol. App. Sci*. 2015; 4; 944-952.
- [51] Rajathi K, Suja S, Kannikaparameswari N. Synthesis and characterization of silver nanoparticles using *Basellarubra* Linn and their in-vitro cytotoxic studies. *Int. J. Chem. Pharm. Sci*. 2015; 3; 1633-1636.
- [52] Stoimenov PK, Klinger RL, Marchin GL, Klabunde KJ. Metal oxide nanoparticles as bactericidal agents. *Langmuir*. 2002; 18; 6679-6686.
- [53] Sondi I, Salopek-Sondi B. Silver nanoparticles as antimicrobial agent: a case study on *E. coli* as a model for Gram-negative bacteria. *J Colloid Interface*. 2004; 275, 177-182.
- [54] Yu H, Chen M, Rice PM, Wang SX, White RL, Sun S. Dumbbell-like bifunctional Au-Fe<sub>3</sub>O<sub>4</sub> nanoparticles. *Nano Lett*. 2005; 5; 379–82.
- [55] Raut RW, Mendhulkar VD, Kashid SB. Photosensitized Synthesis of Silver Nanoparticles Using *Withania somnifera* Leaf Powder and Silver Nitrate. *Journal of Photochemistry and Photobiology B: Biology*. 2014; 132 (2); 45-55.
- [56] Khatoon N, Mishra A, Alam H, Manzoor N, Sardar M. Biosynthesis, characterization, and antifungal activity of the silver nanoparticles against pathogenic *Candida species*. *Bio Nano Sc*. 2015; 5; 65-74.
- [57] Becker RO. Silver ions in the treatment of local infections. *Metal-based drugs*, 1999; 6 (1), 311.
- [58] Chiara R, Letizia F, Ilaria T, Marco R, Ivan M, Chiara G, Warren C, Vincenzo V, Bruno A, Carlo B, Barbara Z. Active Silver Nanoparticles for Wound Healing. *Int. J. Mol. Sci*. 2013; 14 (3); 4817-4840.
- [59] Pedahzur R, Lev O, Fattal B, Shuval HI. The interaction of silver ions and hydrogen peroxide in the inactivation of
- [60] *E. coli*: a preliminary evaluation of a new long acting residual drinking water disinfectant. *Water Sci Technol*. 1995; 31 (1); 123-129.
- [61] Edison TJI, Sethuraman MG. Instant Green Synthesis of Silver Nanoparticles using *Terminalia chebula* Fruit Extract and Evaluation of Their Catalytic Activity on Reduction of Methylene Blue. *Process Biochemistry*. 2012; 47 (12), 1351-1357.
- [62] Jebakumar TN, Immanuel E, Sethuraman MG. Electro catalytic reduction of benzyl chloride by green synthesized silver nanoparticles using pod extract of *Acacia nilotica*. *ACS Sustainable Chemistry and Engineering*. 2013; 10 (2), 1326–1332.
- [63] Sathishkumar G, Gobinath C, and Wilson A, Sivaramakrishnan S. *Dendrophthoe falcata* (Lf) Ettingsh (Neem mistletoe): A potent bio resource to fabricate silver nanoparticles for anticancer effect against human breast cancer cells (MCF-7). *Spectrochim. Acta Part A Mol. Biomol. Spectrosc*. 2014; 128 (1); 285–290.
- [64] Mishra A, Mehdi SJ, Irshad M, Ali A, Sardar M, Moshahid M, Rizvi A. Effect of biologically synthesized silver nanoparticles on human cancer cells. *Sci. Adv. Mater*. 2012; 4 (1), 1200–1206.

- [65] Kuppusamy P, Ichwan SJ, Al-Zikri, Suriyah WH, Soundharrajan I, Govindan N, Maniam GP, Yuso, MM. In vitro anticancer activity of Au, Ag nanoparticles synthesized using *Commelina nudiflora* L. aqueous extract against HCT-116 colon cancer cells. *Biol. Trace Elem. Res.* 2016;173 (1); 297–305
- [66] Nayak D, Pradhan S, Ashe S, Rauta PR, Nayak B. Biologically synthesised silver nanoparticles from three diverse family of plant extracts and their anticancer activity against epidermoid A431 carcinoma. *J. Colloid Interface Sci.* 2015; 457 (2); 329–338.
- [67] Mittal AK, Thanki K, Jain S, Banerjee UC. Comparative studies of anticancer and antimicrobial potential of bio- inspired silver and silver-selenium nanoparticles. *Appl. Nanomed.* 2016; 1 (1); 1–6.
- [68] Birbrair A, Zhang T, Wang ZM, Messi ML, Olson JD, Mintz AO, Delbono O. Type-2 pericytes participate in normal and tumoral angiogenesis. *Am. J. Physiol. Cell Physiol.* 2014; 307 (2); 25–38.
- [69] Bhat TA, Singh RP. Tumor angiogenesis—a potential target in cancer chemoprevention. *Food Chem. Toxicol.* 2008; 46 (8), 1334–1345.
- [70] Folkman J. Role of angiogenesis in tumor growth and metastasis. (Seminars in Oncology); Elsevier., Amsterdam, The Netherlands, 2002; p.15–18
- [71] Collins K, Jacks T, Pavletich NP. The cell cycle and cancer. *Proc. Natl. Acad. Sci.* 1997; 94, 2776–2778.
- [72] Chang YJ, Tai CJ, Kuo LJ, Wei PL, Liang HH, Liu TZ, Wang W, Tai CJ, Ho YS, Wu CH. Glucose-regulated protein 78 (GRP78) mediated the easy to curcumin treatment on hepatocellular carcinoma. *Ann. Surg. Oncol.* 2011; 18 (1); 2395–2403.
- [73] Mao X, Seidlitz E, Truant R, Hitt M, Ghosh HP. Re-expression of TSLC1 in a non-small-cell lung cancer cell line induces apoptosis and inhibits tumor growth. *Oncogene.* 2004; 23 (4); 5632–5642.
- [74] Bharadwaj P. S. Silver or silver nanoparticle a safety or a risk. *J. Environ. Res. Dev.* 2012; 7 (2), 452–456.
- [75] He Y, Du Z, Ma S, Liu Y, Li D, Huang H, Jiang S, Cheng S, Wu W, Zhang K. Effects of green-synthesized silver nanoparticles on lung cancer cells in vitro and grown as xenograft tumors in vivo. *Int. J. Nanomed.* 2016; 11 (1); 1879